



**NFPA 701 - 2004 FIRE TESTS FOR  
FLAME-RESISTANT TEXTILES AND FILMS  
METHOD 1**

**Client:** Ferrari Textile Corp.  
**Address:** Ferrari Textile Corp.  
1510 SW 5<sup>th</sup> Court  
Pompano Beach, FL 33069  
U.S.A.

**Received Date:** April 30, 2010  
(This specimen was received in good condition.)

**Test Date:** May 7, 2010  
**Report Date:** May 24, 2010

**Project No:** 100119678MID-004

**Sample Identification:** MID 1004301109-001

**Description:** Soltis 92

**Sample Preparation:** The samples were prepared by client

**Weight:** 25.50 grams.  
**Specimens Dimensions:** 5.9 in. x 15.75 in. x 0.02 in.

**This Test Witnessed by:** N/A  
**Environmental Conditions:** 70°F and 42% r.h.

**SUMMARY OF TEST PROCEDURE:**

Ten specimens are cut with the long dimension parallel to the lengthwise direction of the material and conditioned for at least 30 min. at 220± 5°F (105± 3°C) before testing. The specimens are removed from the oven one at a time and tested within 2 minutes. The top edge of the specimen is attached to a pin bar so that the specimen is centered on the pin bar and the long dimension of the specimen is in the vertical position with 0.75" binder clips attached to the specimen at each bottom corner. A specified test flame is applied to the bottom center of the specimen for 45 sec. and then removed.

**Intertek Testing Services NA, Inc.**  
8431 Murphy Drive  
Middleton, WI 53562  
Telephone: 608-836-4400 Fax: 1-608-831-9279  
e-mail: [www.intertek-etlsemko.com](http://www.intertek-etlsemko.com)

**TEST CRITERIA:**

The average weight loss of ten specimens shall not be greater than 40%. The percent weight loss of any individual specimen can not exceed the mean percent weight loss value plus three standard deviations of the percent weight loss. The average floor flame of ten specimens shall not be greater than 2 seconds.

**TEST RESULTS**

Sample No.	Wt. Before (grams)	Wt. After Test (grams)	Percent Wt. Loss	AfterFlame (sec.)	Floor Flame (sec.)
1	25.55	22.0	0.14	0	0
2	25.31	14.0	0.45	0	6
3	25.38	20.1	0.21	0	0
4	25.73	24.2	0.06	3	0
5	25.11	18.8	0.25	0	0
6	25.54	21.2	0.17	0	0
7	25.59	20.4	0.20	0	0
8	25.41	22.0	0.13	4	0
9	25.78	20.4	0.21	0	0
10	25.56	21.3	0.17	0	0
Average	25.50	20.4	0.20	1	1

The mean percent weight loss value plus three standard deviations of the percent weight loss is **49**.

**Conclusion:**

**THE SPECIMEN PASSED THE TEST CRITERIA.**

*This report is for the exclusive use of Intertek's Client and is provided pursuant to the agreement between Intertek and its Client. Intertek's responsibility and liability are limited to the terms and conditions of the agreement. Intertek assumes no liability to any party, other than to the Client in accordance with the agreement, for any loss, expense or damage occasioned by the use of this report. Only the Client is authorized to copy or distribute this report and then only in its entirety. Any use of the Intertek name or one of its marks for the sale or advertisement of the tested material, product or service must first be approved in writing by Intertek. The observations and test results in this report are relevant only to the sample tested. This report by itself does not imply that the material, product, or service is or has ever been under an Intertek certification program.*

This report contains a total of three pages.



---

Andrew Maximiuk  
Lab Technician II

May 24, 2010

Reviewed and approved:

---

Stewart Relyea  
Team Leader

May 24, 2010